

971-9119

PROTEC® METAL CONDITIONER

PRODUCT DESCRIPTION

Protec Metal Conditioner is a phosphoric acid based metal pretreatment solution. It facilitates removal of oil, grease and rust as well as chemically etching the metal surface to provide optimum adhesion of subsequent primer coats.

PRODUCT

Protec Metal Conditioner

971-9119

APPLICATION & USE



1. Depending on the amount of rust and grease present, dilute 971-9119 *Protec* Metal Conditioner from one to three parts by volume with water only.
2. Apply by brush, scouring pad or mop and rub with fine steel wool to loosen rust deposits.
 - Avoid heavy applications of 971-9119 *Protec* Metal Conditioner.
3. Allow to react for 10-15 minutes before wiping excess material from the surface with clean, lint free cloths.
4. Wipe dry with a fresh clean, lint free cloth.
 - When applying two pack primers, rinse the treated surface thoroughly with clean water and wipe dry as quickly as possible.

CAUTION - Do not leave the treated surface unprimed for more than 30 minutes.

HEALTH AND SAFETY

Please refer to Safety Data Sheets (SDS) for full Health and Safety details, as well as product can

This product is for professional use only.
The information given in this sheet is for guidance only. Any person using the product without first making further inquiries as to the suitability of the product for the intended purpose does so at his or her own risk and we can accept no liability for the performance of the product or for any loss or damage (other than death or personal injury resulting from our negligence) arising out of such use. The information contained in this sheet is liable to modification from time to time in the light of experience and our policy of continuous product development.
Drying times quoted are average times at 25°C/77°F. Film thickness, humidity and shop temperature can all affect drying

PPG Industries Australia Pty Ltd, 14 McNaughton Rd
Clayton, VIC 3168 Australia

EMERGENCY RESPONSE NUMBER, Australia: 1800 883 254

PPG Industries New Zealand Pty Ltd, 5 Vestey Dr, Mt Wellington
Auckland, New Zealand

EMERGENCY RESPONSE NUMBER, New Zealand: 0800 000 096

times.

Protec and the *Protec Logo* are registered trademarks of Protec Pty Ltd.



」