



990-9285 ANTI-SLIP ADDITIVE

PRODUCT DESCRIPTION

990-9285 is a specialised additive designed to impart non-slip properties when added to topcoats. It has been independently tested to AS 4586:2013 Slip resistance classification of new pedestrian surface materials, Appendix A - Wet Pendulum Test and AS 4586:2013 Slip resistance classification of new pedestrian surface materials, Appendix D - Oil Wet Inclining Platform Test. The addition levels recommended below are to achieve a Wet Pendulum Test rating P5 and Oil Wet Inclining Platform Test rating R12.

PRODUCT

Anti-Slip Additive

990-9285

SPRAY APPLICATION

Mix the Topcoat colour as per Technical Data Sheet Instructions.

By weight using a scale, weigh the mixed material and to 1000gm add 7.5% by weight 990-9285 Anti-Slip Additive, which will equate to 75 gm of 990-9285 Anti-Slip Additive, stirring slowly during addition to ensure no lumps form.

Apply 2 full coats allowing 10-15 minutes flash off time or until the first coat has a complete eggshell appearance.

ROLLER APPLICATION

Mix the Topcoat colour as per Technical Data Sheet Instructions.

By weight using a scale, weigh the mixed material and to 1000gm add 5% by weight 990-9285 Anti-Slip Additive, which will equate to 50 gm of 990-9285 Anti-Slip Additive, stirring slowly during addition to ensure no lumps form.

For similar results to spray application, a 10mm Micro Fibre Roller is recommended.

HEALTH AND SAFETY

Please refer to Safety Data Sheets (SDS) for full Health and Safety details, as well as product can labels.

This product is for professional use only.
The information given in this sheet is for guidance only. Any person using the product without first making further inquiries as to the suitability of the product for the intended purpose does so at his or her own risk and we can accept no liability for the performance of the product or for any loss or damage (other than death or personal injury resulting from our negligence) arising out of such use. The information contained in this sheet is liable to modification from time to time in the light of experience and our policy of continuous product development.
Drying times quoted are average times at 25°C/77°F. Film thickness, humidity and shop temperature can all affect drying times.

**PPG Industries Australia Pty Ltd, 14 McNaughton Rd
Clayton, VIC 3168 Australia**
EMERGENCY RESPONSE NUMBER, Australia: 1800 883 254

**PPG Industries New Zealand Pty Ltd, 5 Vestey Dr, Mt Wellington
Auckland, New Zealand**
EMERGENCY RESPONSE NUMBER, New Zealand: 0800 000 096

PPG Logo is a registered trademark of PPG Industries Ohio, Inc.
Protec is a registered trademark of Protec Pty Ltd.
Startline is a registered trademark of PPG Industries Australia Pty Ltd.