



EPS ETCHPRO

PRODUCT DESCRIPTION

Commercial Performance Coatings EtchPro is a single pack, epoxy resin based etching primer with excellent adhesion to a large number of metal surfaces including mild steel, zinc plated steel, zincanneal, aluminium, galvanized iron, brass, copper, stainless steel, lead and alloys.

It can be used as a low film build conventional etching primer or as a metal primer at higher film builds.

Utilizing the SELEMIX® universal tinter system, Commercial Performance Coatings EtchPro is available in a range of colours.

PRODUCTS

EtchPro Mixed Colour	EPS Binder + Tinter
Factory Packs	N35 Light Grey N61 Black N14 White Ferrous substrates only
Reducers	EPR20 Etch Primer Reducer Normal
Cleaners	AA-6822 PROTEC® Heavy Duty Wax & Grease Remover

SUBSTRATES & PREPARATION



Commercial Performance Coatings EtchPro Primer Surfacer can be applied over the following substrates once they have been prepared as follows:



SUBSTRATE

Bare Steel
Phosphated Steel
Galvanized Steel
Stainless Steel
Brass
Aluminium

PREPARATION

STARTLINE® P150 - dry
Startline Scourer
Startline Scourer
Startline P280-P320 - dry
Startline P280-P320 - dry
Startline Scourer

Bare Aluminium surfaces should be thoroughly cleaned using AA-6822 *Protec* Heavy Duty Wax & Grease Remover before sanding. Use a high grade scouring pad to remove heavy areas of grease and imperfections in a wipe on, wipe off motion using clean rags.

Once dry, thoroughly abrade the surface using *Startline* P240 or P320.

Once sanded, the aluminium should be blown down and cleaned with a 1:1 mix of 207 Methylated Spirits and water, using a wipe on, wipe off motion. This must be repeated until no residue shows on the cleaning cloths.

Continued over page...


NOTE: The prepared aluminium must be primed within six hours of the preparation process. Failure to comply will allow the aluminium to re-oxidise.

Not recommended for use on abrasively blasted surfaces.

Before and after any sanding operation, the substrate must be thoroughly degreased using AA-6822 *Protec* Heavy Duty Wax & Grease Remover to remove all traces of dirt, oil, grease, silicone, wax etc.

Substrates other than those stated above should be tested before use, to ensure that the performance of this product is suitable for its intended use.

MIXING RATIO BY VOLUME




PRODUCT

EtchPro Mixed Colour
Reducer

PARTS

100
Up to 10%

SPRAY VISCOSITY



20 - 23 seconds (DIN 4) at 25°C

SPRAYGUN



CONVENTIONAL, HVLP

SETUP

- GRAVITY 1.4 mm - 1.6 mm
- SUCTION 1.6 mm - 1.8 mm

SPRAY PRESSURE

- CONVENTIONAL 2.0 - 2.5 bar (200 - 300 kPa, 30 - 36 psi)
- HVLP / RP 2 - 3 bar

APPLICATION & FLASH OFF



Apply 1 - 2 wet, even coats

Allow 3 - 10 minutes flash off between coats at 25°C

Note: Do not apply at temperatures less than 10°C, when the relative humidity exceeds 80%, or if the surface temperature is within 3°C of the dew point.

DRYING TIMES



AIR DRY (25°C)

- DUST FREE: 3 - 5 minutes
- DRY TO HANDLE: 20 minutes

Note: Drying times can vary dependent on temperature, flash off between coats, film builds and number of coats applied.

RECOAT



Allow 1 to 4 hours drying time before recoating, this will depend on ambient temperature, must be touch dry before topcoat. Recommendations are based on 25°C ambient temperature.

TOTAL DRY FILM BUILD

15 - 20 µm

TECHNICAL PARAMETERS

VOLUME SOLIDS (RFU)

13 - 19%, depending on colour

COVERAGE

6.5 - 13.0 metres squared per litre (m²/L)

EQUIPMENT CLEANING

After use, clean all equipment thoroughly with cleaning solvent or thinner.

HEALTH AND SAFETY

Please refer to Safety Data Sheets (SDS) for full Health and Safety details, as well as product can labels.

This product is for professional use only.
The information given in this sheet is for guidance only. Any person using the product without first making further inquiries as to the suitability of the product for the intended purpose does so at his or her own risk and we can accept no liability for the performance of the product or for any loss or damage (other than death or personal injury resulting from our negligence) arising out of such use. The information contained in this sheet is liable to modification from time to time in the light of experience and our policy of continuous product development.
Drying times quoted are average times at 25°C/77°F. Film thickness, humidity and shop temperature can all affect drying times.

**PPG Industries Australia Pty Ltd, 14 McNaughton Rd
Clayton, VIC 3168 Australia**

EMERGENCY RESPONSE NUMBER, Australia: 1800 883 254

**PPG Industries New Zealand Pty Ltd, 5 Vestey Dr, Mt Wellington
Auckland, New Zealand**

EMERGENCY RESPONSE NUMBER, New Zealand: 0800 000 096

PPG Logo and Selemix are registered trademarks of PPG Industries Ohio, Inc.
Protec is a registered trademark of Protec Pty Ltd.
Startline is a registered trademark of PPG Industries Australia Pty Ltd.